LABOSPORT INDIA

Internal Test Program Results

SYNTHETIC FOOTBALL TURF

Maverick Turf SDN BHD

No.7 -1, Lorang Batu Nilam 3B, Bandar Bukit Tinggi Klang, Malaysia

Product name Maverick Turf Football Grass

Tested on 29/01/2019

Report no. LSIND-R19003-A2

Specifications

Colour Green

Tufting Fibrillated straight yarn

Pile height 50 mm

SBR Infill 0.5 to 2 mmSand Infill 0.5 to 1 mmMass per unit area $2,327 \text{ g/m}^2$

Tuftperunitarea; gauge 9,300 /m²; 5/8 inch



Shock Absorption: 58.4%

Vertical Deformation: 8.8 mm

Rotational Resistance: 34 Nm

Vertical Ball Rebound: 0.90 m





Mathieu Leon
Deputy General Manager
Labosport India Pvt Ltd

Labosport does not make any warranty (expressed or implied) or assume any liability or responsibility to the user, reader or other third party, for the accuracy, completeness or use of, or reliance on, any information contained within the Labosport internal test program, or for any injuries, losses or damages (including without limitation, equitable relief) arising from such use or reliance. Labosport authorizes the user to view, use and reference this program. This document may also be reproduced, displayed or distributed, including displayed on a website or in a networked environment. In exchange for this authorization, the user agrees that all copyrights and other proprietary notices contained in this program remain the exclusive property of Labosport. The user also agrees not to sell or modify this program in any way for any public or commercial purpose. As an additional condition of use, the user agrees not to sue, and agrees to waive and release Labosport and its employees from any claim, demand and cause of action for any injuries, losses or damages (including without limitation, equitable relief) that may now or hereafter have a right to assert against such parties as a result of use of, or reliance on, this program.